

Local Phone: 203-575-9220

PRODUCT DATA SHEET

Business Hours: 8 am - 5 pm

Toll Free: 1-800-537-7663

2001 Inc.
P.O. BOX 2557 Waterbury, CT 06723-2557
325 THOMASTON AVE.
WATERBURY, CT 06702

Emergency Telephone
1-800-255-3924

PDS Date 03/01/05

Supercedes All Previous Publications

Page 1 of 1

PRODUCT NAME AND SYNONYMS: 2001 ONE-PART POURABLE SEALER

Typical Properties And Characteristics:

<u>Property</u>	<u>Typical Value</u>
Specific Gravity:	1.4 (11.6 lbs/gallon)-1.5 (12.5 lbs/gallon) (1.39 kg/liter) (1.50 kg/liter)
Viscosity (Brookfield RTV), cps	Self leveling 20,000-50,000
Color:	Black
Odor:	Mild Ester Smell (Mint) When Wet. Odorless When Dry
Elongation @ Break, % -(7 Day Ambient Cure)	ASTM D-0412 450
Hardness, (Shore A)	ASTM C-0661 25-35
Tack Free Time -@70 Degrees F. (21 degrees C)	ASTM C-0679 Less than 1 Hour
Low Temperature Flex Shrinkage (14 day cure)	PASS Minus 20 degrees F. (Minus 29 degrees C) No Measurable Shrinkage
Service Temperature	ASTM 2453 Minus 40 Degrees F to 200 Degrees F. (Minus 40 degrees C to 93 degrees C)
Long Term Weatherability -98 Cycles @12 hours/cycle -Condensate Exposure: 4 hrs @122°F (50°C) -U.V. Exposure-8 hrs @158°F (70°C)	ASTM G53 No Cracking or Cracking
Packaging Weight Per Carton Shelf Life (Unopened Container)	4-0.5 Gallon Pouches per Bucket (4-2 liter) 29 lbs./bucket (13.15 kg) 12 Months

DISCLAIMER: The information contained herein is, to the best of our knowledge and belief, accurate. However, since the conditions of handling and use are beyond our control, we make no guarantee of results, and assume no liability for damages incurred by use of this material. It is the responsibility of the user to comply with all applicable federal, state and local laws and regulations. Prepared By: 2001 Inc.